

# Luster-On Products

## Technical Data Sheet

### **LUSTER-ON 132RW** **Multi-metal Spray or Soak Cleaner**

#### **I. GENERAL DESCRIPTION**

Luster-On 132RW is a non-etch cleaner for aluminum and a general purpose cleaner for brass and steel. It removes processing oils, shop dirt, marking inks, etc., while retaining the original luster. Luster-On 132RW is recommended as an aluminum cleaner prior to anodizing, chromating, polishing or etching operations. It is used to clean zinc or copper alloys prior to chemical polishing, chromating or electroplating. Luster-On 132RW safely removes soils from stainless steel, steel, brass, aluminum, copper, magnesium, and glass with excellent rinsing ability.

#### **READ MATERIAL SAFETY DATA SHEET BEFORE USING THIS PRODUCT**

#### **II. BATH MAKE-UP**

The cleaner should be made up by filling the tank half full with water and heating to 100°-120°F. The calculated amount of Cleaner 132RW is added slowly and carefully with stirring or other agitation. When all the cleaner has dissolved, bring the solution up to working level with water and heat to operating temperature.

#### **III. OPERATING CONDITIONS**

The cleaner should be operated in the temperature range of 130°-160°F. at a concentration of 4 to 8 ounces per gallon. The immersion time will vary from 5 to 15 minutes depending upon the temperature, concentration and the nature of the soil to be removed.

**Luster-On Products, Inc., Springfield, MA – 800-888-2541, Fax 413-731-5549**  
[www.luster-on.com](http://www.luster-on.com) E-MAIL [sales@luster-on.com](mailto:sales@luster-on.com)

## **LUSTER-ON 132RW**

### **IV. HELPFUL COMMENTS**

Has good hard water tolerance.  
Specially inhibited to prevent attack on aluminum.  
Some agitation is desirable, but not mandatory.  
Has good rinsability.

### **V. EQUIPMENT**

Steel tank with steam, gas or electric heating.

### **VI. PACKAGE**

400-pound poly lined fiber drum.

### **VII. STORAGE**

Keep covered when not in use. Keep dry.

### **VIII. DISPOSAL**

Dilute, then neutralize with an acidic material and discharge in accordance with Federal, State, and Local Regulations.

### **IX. SAFETY AND HANDLING PRECAUTIONS**

Moderately alkaline industrial product.

Avoid contact with eyes, skin and clothing.

Wear safety goggles, rubber gloves and other suitable protective clothing when handling.

Avoid inhalation of mist.

Use with adequate ventilation.

Do not take internally.

Keep container closed when not in use.

In case of spills and leakage, flush area with plenty of water.

Store in a cool place out of direct sunlight.

**WARNING!** Causes irritation of eyes. Prolonged skin contact causes irritation. Harmful if swallowed. Do not get in eyes. Avoid prolonged skin contact. Wash thoroughly after using.

## **LUSTER-ON 132RW**

### **IX. SAFETY AND HANDLING PRECAUTIONS (Continued):**

#### **FIRST AID IN CASE OF CONTACT**

**FOR EYES:** Immediately flush eyes with plenty of water for at least 15 minutes. Hold eyelids apart while flushing to insure contact of water with all surfaces of eyes and lids. **Get immediate medical attention!**

**FOR SKIN:** Immediately flush area with plenty of water for at least 15 minutes. Remove contaminated clothing and shoes and wash before reuse. **Get immediate medical attention!**

**IF SWALLOWED:** Wash out mouth thoroughly with water. Give several glasses of water to drink followed by diluted vinegar, lemon juice or other citrus fruit juice. **Get immediate medical attention!**

**IF INHALED:** Remove from exposure. In case of severe overexposure, **get immediate medical attention!**

**KEEP OUT OF REACH OF CHILDREN**

**FOR INDUSTRIAL USE ONLY**

This product is sold for industrial use only. Our suggestions for its use are based upon tests and procedures, which from experience we believe to be reliable. Since the use is beyond our control, neither we nor our distributors can assume responsibility, either expressed or implied for the results and/or for violation of any patents or any claims resulting from such use.

**LUSTER-ON®** is a registered trademark of **LUSTER-ON PRODUCTS, INC.**

REV. 06/26/00

# Luster-On Products

## Technical Data Sheet

### **CONTROL PROCEDURE FOR LUSTER-ON 132RW**

1. Pipette a 10 ml sample into a 250-ml Erlenmeyer flask.
2. Dilute with 50-ml of water.
3. Add 5 drops of Congo Red Indicator
4. Titrate with 1.0N Hydrochloric Acid until the color changes from orange to red.

#### **Calculation**

ml of 1.0N HCl X 0.46 = oz/gal. Luster-On 132RW.